



SURFACE - BLOTTED SEAL COAT TYPE C: THE INITIAL SEAL AND FINAL SEAL SHALL CONFORM TO THE REQUIREMENTS OF AASHTO M208 @ 0.17 GAL./SQ. YD. WITH 15 LBS. OF NO 8P STONE/SQ. YD. EACH. THE BLOT SEAL SHALL CONFORM TO THE REQUIREMENTS OF AASHTO M208 @ 0.15 GAL./SQ. YD. WITH 10 LBS. OF FINE AGGREGATE GRADE B SAND PER SQ. YD.

DATE MAY 2004 HANOVER DPU	TYPICAL SECTION FOR REPAIR OF OPEN CUT AFTER PLACEMENT OF SEWER IN SURFACE TREATED ROAD WHERE A BASE (EXCEPT CONCRETE OR PLANT MIX) IS PRESENT	DRWG. NO. <b>PAV-2</b>
------------------------------------	--	---------------------------