



* REPLACEMENT OF PAVEMENT SHALL BE FROM EDGE OF PAVEMENT TO EDGE OF PAVEMENT.

SURFACE - BLOTTED SEAL COAT TYPE C: THE INITIAL SEAL AND FINAL SEAL SHALL CONFORM TO THE REQUIREMENTS OF AASHTO M208 @ 0.17 GAL./SQ. YD. WITH 15 LBS. OF NO 8P STONE/SQ. YD. EACH. THE BLOT SEAL SHALL CONFORM TO THE REQUIREMENTS OF AASHTO M208 @ 0.15 GAL./SQ. YD. WITH 10 LBS. OF FINE AGGREGATE GRADE B SAND PER SQ. YD.

DATE
MAY 2004
HANOVER
DPU

TYPICAL SECTION FOR REPAIR OF OPEN CUT AFTER PLACEMENT OF
SEWER IN SURFACE TREATED ROAD
(APPLIES TO PARALLEL INSTALLATION & SERVICE CROSSINGS)

DRWG. NO.
PAV-3